



8400

Cross-Link Barrier Coating

Product Description

MCM #8400 Cross-Link Coating is specifically designed for roofs and walls where complete waterproofing is needed. It is manufactured with ceramic spheres and a crosslink resin to create the best quality waterproofing coating available. Not only is it the best waterproofing coating but also an excellent insulator. It is flash rust and mildew resistant. It's flexibility and high solids allow it to withstand extreme weather conditions.

Product Features

- Extremely Flexible
- Excellent UV resistance
- Bridges hairline cracks
- Resists ponding water
- Can be tinted to any color
- Reduces energy costs
- Easy clean up
- Excellent flow & level
- Easy application

Recommended Uses

- Metal
 - Galvanized
 - Masonry
 - Foam
 - Asphalt & Shingle roofs
 - Rubber Roofs
- Also recommended for masonry walls including block, stucco and plaster.

Surface Preparation

All surfaces must be clean, sound and dry. Dull glossy surfaces by sanding. Fill all cracks using a Dycro or similar patching compound. Remove mildew. Chalky surfaces should be sealed with our #40 sealer. Allow 30 days for new stucco to cure before coating.

Application

May be applied by brush, roller or spray. Best application is achieved by pouring a small amount on roof and spread with a thick nap roller. If spraying it is recommended to use a large orifice tip. On walls apply generously by rolling or spray. Avoid condensation during application

Spreading Rate

Should be applied at 75-100 square feet per gallon depending on surface porosity and application methods. Coverage can vary greatly.

Drying Time

Dries to touch in 1-4 hours depending on millage. Dry time may vary depending on temperature, humidity

Clean Up

Clean hands, tools and equipment promptly with warm soapy water.

Characteristics

Finish: Low Luster
Color: White & mixed colors
Generic Type: Cross Link
Solvent: Water
Weight per Gal: 12.0 lbs

Physical Properties

Wind Driven Rain Test:
Passes ASTM D6904-03
Tensile Strength:
337 PSI ASTM D2370
14 Days Cure
Elongation:
353% ASTM D2370
Water Vapor:
22.9 perms ASTM D1653
Adhesion Test:
Passes ASTM D6370

CAUTION!
KEEP FROM FREEZING.
Do not take internally. Close container after each use. USE WITH ADEQUATE VENTILATION.
KEEP OUT OF REACH OF CHILDREN

LIMITATION OF LIABILITY
This information is based on technical data believed to be accurate and reliable, but is furnished without any express or implied warranties. MCM Paints will replace such quantity of this paint that is proved to be defective. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.

WARNING! Removal of old paint by sanding, scraping or other means may generate fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of properly fitted protective equipment such as a respirator and proper containment and cleanup. For more information call the national Lead Information Center at 1-800-424-LEAD.